

In the claims:

For the Examiner's convenience, all pending claims are presented below with changes shown in accordance with the mandatory amendment format.

1. (Currently Amended) A process, comprising:
providing a device substrate having a dielectric layer thereon;
removing a portion of the dielectric layer to create an opening; [[.]]
forming an interface layer within the opening;
forming a silver layer overlying the interface layer; [[and]]
annealing the substrate to form an intermetallic layer between the silver layer and the
interface layer, in which the silver layer is in intimate contact with the
intermetallic layer; and
forming a protection layer overlying the silver layer which is thick enough to prevent the
silver layer from diffusing into other materials.
2. (Original) The process of claim 1, further comprising removing portion of the silver layer, intermetallic layer, and the interface layer overlying the dielectric layer to form a smooth surface.
3. (Original) The process of claim 1, wherein the interface layer comprises an adhesion layer and a diffusion barrier layer overlying the adhesion layer.

4. (Original) The process of claim 3, wherein the diffusion barrier layer comprises titanium nitride or tantalum nitride.
5. (Original) The process of claim 3, wherein the adhesion layer comprises titanium, tungsten, aluminum, or titanium nitride.
6. (Original) The process of claim 1, wherein the interface layer is formed using sputter deposition process.
7. (Original) The process of claim 1, wherein the silver layer is formed using sputter deposition process.
8. (Original) The process of claim 1, wherein the substrate is annealed at an ambient temperature of approximate 400 degree Celsius for a period of approximate one hour.
9. (Original) The process of claim 2, wherein the removing comprises a chemical-mechanical-polishing (CMP) process.

10-23. (Cancelled)

24. (Currently Amended) An interconnect structure, comprising:
 - a device substrate;
 - an interface layer overlying the device substrate;
 - a silver layer overlying the interface layer;

a protection layer overlying the silver layer which is thick enough to prevent the silver layer from diffusing into other materials; and
a dielectric layer overlying the protection layer.

25. (Original) The interconnect structure of claim 24, wherein the interface layer comprises an adhesion layer and a diffusion barrier layer overlying the adhesion layer.

26. (Original) The interconnect structure of claim 25, wherein the diffusion barrier layer comprises titanium nitride or tantalum nitride, and wherein the adhesion layer comprises titanium, titanium nitride, aluminum, or tungsten.

27. (Original) The interconnect structure of claim 24, wherein the protection layer comprises titanium, titanium nitride, or tungsten.

28. (Currently Amended) An interconnect structure, comprising:

a device substrate;

a dielectric layer overlying the device substrate, the dielectric layer having a cavity therein;

an interface layer overlying the dielectric layer, the interface layer having a thickness insufficient to completely fill the cavity; [[and]]

a silver layer overlying the interface layer, the silver layer having a thickness sufficient to completely fill the cavity; and

a protection layer overlying the silver layer which is thick enough to prevent the silver layer from diffusing into other materials.

29. (Original) The interconnect structure of claim 28, wherein the interface layer comprises an adhesion layer and a diffusion barrier layer overlying the adhesion layer.

30. (Original) The interconnect structure of claim 29, wherein the diffusion barrier layer comprises titanium nitride or tantalum nitride, and wherein the adhesion layer comprises titanium, titanium nitride, aluminum, or tungsten.